

Wet Room Paint 30

Properties

Semi-matte wet room paint.

Use

Bathrooms, toilets and similar wet rooms.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning and sanding.
 Remove dirt, grime, grease and chalking materials by cleaning.
 Remove lime and soap residue.
 Sand hard, slippery surfaces flat.
 Cracks, holes and irregularities must be spackled with suitable joint filler/spackle.
 Absorbent and porous substrate primed with Sealer.
 Install glass tissue/glass felt using a Wet Room Primer.
 Apply wet room paint 2 times. Some shades require an extra treatment.

Application

Brush, roller or spray
 Decide your choice of tool/utensil depending on the finish
 Apply wet on wet and finish by brushing/rolling in the same direction
 Always use the same batch number on contiguous/unbroken surfaces
 Differences in surface structure can result in colour deviation
 Cold/heat can affect the viscosity of the material
 Material temperature for spray painting, min. 12°C
 Condensation must be prevented during drying/curing
 Cold and increased humidity extends drying time, full curing and recoat interval
 Increased temperature and low atmospheric humidity reduce drying time and full curing
 Always perform a test treatment for a check and acceptance of adhesion and result

Expected result

Semi-matte, strong surface
 Uniform, smooth texture with clear gloss.
 Withstands cleaning with water, cleaning agents, brush and cloth.
 Strong, especially dark shades are more susceptible to wear and tear than bright shades.
 Coat the surface with care and avoid direct contact with water before the paint is fully cured.

Environmental information

Cleaning of tools: Remove as much paint as possible before cleaning with water and soap.
 Storage: Cool and frost-free.
 NB! See also Product Datasheet.



Storage: Cool, frost free and tightly closed

Technical Data

Product Type	Acrylic paint
Gloss	30;Semi Matte
Density (kgs/l)	1.22
Solids Weight %	49
Solids Vol. %	38
Nominal spreading rate (m ² /ltr.)	7
Min. working temp. during application and drying/curing	Min. +10°C
Drying time at 20° C, 60 % RH (Hours)	3
Recoatable at 20° C, 60 % RH (Hours)	16
Fully cured at 20° C, 60 % RH (Days)	28
Emission acc. to ISO 16000-9:2011 (< µg/m ² h after 28 days)	280
Washability acc. to EN-13300/ISO-11998	Class 1
Cleaning of Tools etc.	Water and soap

Current TDS Version

September 2019