

Robust 10

Product properties

Matt wall paint.

Labelling



Product use

Living rooms, corridors, entrance areas, offices, kitchens, commercial premises, institutions, clinics, retail shops and stairways.

Concrete, lightweight concrete, plaster, bricks, gypsumboards, fiber plaster, cement fiber boards, cement particle boards.

Substrate

Must be clean, dry, solid and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning and sanding.

Remove dirt, grime, grease and chalking materials with Basic Cleaner.

Water blotches or surfaces stained by nicotine or soot must be cleaned with Basic Cleaner and treated with Stop Primer.

Hard, smooth surfaces should be sanded matt and painted with Grip Primer as required.

Cracks, unevenness and holes must be spackled.

Absorbent and porous substrates must be primed with Micro Primer.

Priming is done with Combi Primer.

Apply 1-2 times. Some colours and surfaces require an extra treatment.

Application

Brush, roller or spray.

Decide your choice of tool/utensil depending on the finish.

Apply wet on wet and finish by brushing/rolling in the same direction.

Always use the same batch number on contiguous/unbroken surfaces.

Differences in surface structure can result in colour deviation.

Cold/heat can affect the viscosity of the material.

Material temperature for spray painting, min. 12°C.

Condensation during drying/curing must not occur.

Cold and increased humidity extends drying time, full curing and recoat interval.

Increased temperature and low atmospheric humidity reduce drying time and full curing.

Always perform a test treatment for a check and acceptance of adhesion and result.

Expected result

Matt strong surface with a subdued even structure, distinct gloss and dirt-repellent properties.

Withstands cleaning including spot cleaning with a soft brush, water and cloth.

Strong especially dark shades are more delicate than light by wear and touch.

Chalking from strong shades due to excess pigment may occur.

Does not block strike-through from knots or water-soluble colourants, water stains and nicotine.

Exercise care in loading the surface until the paint is fully cured.

Useful Information

If repairs are needed, remove minor marks and dirt by cleaning.

Spot repairs are carried out with the same material/batch number as originally used.

Spot repairs are expected to be visible to a greater or lesser extent depending on colour, gloss, application method, surface, light and viewing angle.

Larger damages are repaired with edging around corners, joints and the like.

Environmental information

Minimize your paint waste by pre-estimating how much paint you need.

Remove as much paint as possible from tools before cleaning.

Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost free and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Avoid inhalation of spray mist and grinding dust.

Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Product Type	Acrylic paint
Gloss	10;Matte
Density (kgs/l)	1.39
Solids Weight %	60
Solids Vol. %	44
Nominal spreading rate (m²/ltr.)	8
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	4
Fully cured at 20° C, 60 % RH (Days)	28
Washability acc. to EN-13300/ISO-11998	Class 1
Dilution	Water, is usually not diluted
Cleaning of Tools etc.	Water
Country of Origin	Denmark

Current TDS Version

April 2025

Replaces TDS Version

May 2024