

KABRIC Floor Strongcoat Silk

DETALE CPH is a line of exclusive decorative products to take care of the small details. Paints and finishes are inspired by our Nordic design heritage and the changeability of nature.

Product properties

Semi-gloss, robust, PU reinforced acrylic varnish. Recommended for substrates treated with KABRIC Floor exposed to medium functional demands, light pedestrian traffic, use-related wear and light soiling. Highlights the aesthetics and look of the surface.

- **PU reinforced acrylic varnish**
- **Robust**
- **Semi-gloss**



Product use

Living rooms and similar common rooms.
Used on substrates treated with KABRIC Floor.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Vacuum clean and dry with a tightly-wrung cloth.
Apply 3 layers KABRIC Floor Strongcoat Silk using a brush and/or roller.

Application

Brush or roller.
Decide on your mode of application according to the desired finish.
Turn off floor heating while treatment is underway.
After treatment, increase the floor heating gradually.
Apply evenly wet-on-wet, avoiding overlap and pools of varnish.
Always use the same batch number on contiguous/unbroken surfaces.
Cold/heat can affect the viscosity of the material.
Condensation must be prevented during drying/curing.
Cold and increased humidity extend drying time, full curing and recoat interval.
Increased temperature and low atmospheric humidity reduce drying time and full curing.
Always do a treatment test to check acceptance of adhesion and result.

Expected result

Semi-gloss, durable surface with dirt-repellent properties.
Rich finish with optimal coalescence.
Withstands cleaning including the cleaning of stains using a non-abrasive cleaner pH > 2 < 9, water, brush and cloth.
Moisture-related size changes from the substrate can result in visible markings in the finished surface.
Take care placing loads on the surface before the varnish is fully cured.
The surface can be used lightly after 24 hours.

Useful Information

Put felt pads on furniture to minimize marks and scratches.
Protect the surface and areas with a lot of traffic and concentrated wear and tear.

Environmental information

Clean off the paint from tools before cleaning. Bring remains of fluent paint to the local recycling centre. Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage

Cool, frost free and tightly closed

Supplementary Info

Anti-slip according to DIN 51130: R9

Shelf life: 24 months in unopened container.

Technical Data

Density (kgs/l)	1.03
Nominal spreading rate (m²/ltr.)	12
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	2
Fully cured at 20° C, 60 % RH (Days)	7
Cleaning of Tools etc.	Water

Current TDS Version

June 2025

Replaces TDS Version

October 2024