

Wood Lacquer

Product properties

Water-based varnish for indoor use. Provides a beautiful, non-yellowing finish. The surface is robust and easy to clean. Natural Wood Lacquer is available in 3 different gloss levels, silk matt, semi-gloss or gloss.

- **Water-based varnish**
- **Does not yellow**
- **Easy-to-clean**



Labelling



Product use

For use on all light-coloured woods, untreated or previously varnished, such as doors, frames and furniture.

Can also be used on stained woodwork.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Clean with Natural Wood Cleaner.

Sand previously varnished surfaces matt.

After drying, sand with fine sandpaper.

Remove sanding dust.

Do not use in spray application equipment.

Application

Brush or roller.

Stir before use.

Apply in an even layer in the lengthwise direction of the wood.

Coat the surface an additional 1 or 2 times depending on need.

Always carry out a test treatment to verify and accept the adhesion and result.

Expected result

Colourless, robust and easy-to-clean surface.

Cleaning and maintenance

Lacquered surfaces are cleaned with a universal cleaner.

Before the lacquer is worn through, the surface should be recoated with Natural Wood Lacquer.

Before recoating, wash with Natural Wood Cleaner.

Please note!

Do not use Natural Wood Lacquer on floors or similar areas where a durable surface is desired.

Environmental information

Remove as much paint as possible from tools before cleaning.
Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.
Empty and dry packaging should be sorted as plastic.

Storage

Cool, frost free and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.
Avoid inhalation of spray mist and grinding dust.
Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Density (kgs/l)	1.1
Solids Weight %	25
Solids Vol. %	23
Nominal spreading rate (m²/ltr.)	10
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	4
Fully cured at 20° C, 60 % RH (Days)	28
Dilution	Do not dilute
Cleaning of Tools etc.	Water and soap
Country of Origin	Denmark

Current TDS Version

December 2024

Replaces TDS Version

April 2024